

## Technical Data Sheet

### Headcel® HPMC 60HD15

#### 1.0 Description

Headcel® HPMC 60HD15 is low viscosity Hydroxypropyl Methyl Cellulose (HPMC) which is designed for using in a wide range of pharmaceutical applications.

#### 2.0 Physical Analysis

Appearance	:	White to slightly off-white fibrous or granular powder.
Identification A to E	:	Conform
Solution appearance	:	Conform
Methoxy	:	28.0-30.0%
Hydroxypropoxy	:	7.0-12.0%
Loss on drying	:	5.0% Max
Residue on ignition	:	1.5% Max
pH	:	5.0-8.0
Apparent viscosity	:	12.0-18.0cps
Particle size	:	Min. 98% pass through 100 mesh

#### 3.0 Heavy Metals

Heavy Metal	:	≤10ppm
Arsenic	:	≤3ppm
Lead	:	≤3ppm
Mercury	:	≤1ppm
Cadmium	:	≤1ppm

#### 4.0 Micro bacteria

Total plate count	:	≤1000cfu/g
Yeast and Mould	:	≤100cfu/g
Coli form	:	Absent/g
Salmonella	:	Absent/g

#### 5.0 Packaging

25kg fibre drum with inner liner.

#### 6.0 Regulation

Meets all requirements of EP, JP, NF, ChP for the monograph Hydroxypropyl Methyl Cellulose 2910.

The information supplied is presented in good faith and has been derived from sources believed to be reliable. Since conditions of use are beyond our control, all risks are assumed by the user. No representation is expressed or implied, and nothing herein shall be construed as permission or recommendation to practice a patented invention without license.

Distributed by: